

# **CREATIV PLASTIC & MINIATURES**

# **COLD WELDING SPECIAL FORMULA**



#### PRODUCT DESCRIPTION

UHU Creativ Plastic & Miniatures with a strong special cold welding formula for the perfect assembly of many hard and soft plastics and various types of miniatures. Ideal for making doll houses, collages, sculptures, objects in Plexiglas®, decorating yogurt pots, and much more. Also suitable for modelling.

### FIELD OF APPLICATION

Attains an excellent bond strength on numerous types of plastics such as polystyrene and high impact polystyrene types (ABS, SAN, SB, ASA), PVC hard. Limited application on Plexiglas® (PMMA), Celluloid®, cellulose ester (CN, CAB), polycarbonate (PC). Phenolic resins (Bakelite®), melamine resins (Resopal®), glass fibre reinforced polyester, polyurethane (PUR) and epoxide resins (EP) can be glued as well. Glues also materials such as wood, paper, cardboard, leather, metals, glass, ceramics. Not suitable for polyamide (PA), acetal resin (POM) polyethylene (PE), polypropylene (PP), polytetrafluoroethylene (PTFE), silicons (Si), Styropor® and not suitable for leather used for clothing.

# **PROPERTIES**

- · Strong cold welding formula
- · For many hard and soft plastics
- · Fast bonding
- · Colourless

#### **PREPARATION**

**Surface Requirements:** The areas to be glued must be dry and free of any dust or grease.

### **APPLICATION**

#### **Directions for use:**

Depending on the requirement, apply to one or both of the materials to be joined and stick together immediately. An initial bond strength is attained after 5 - 10 minutes. The high bond strength is attained by melting the plastic surface. For this reason, the adhesive should only be applied in small quantities to thin walled plastics.

**Stains/residue:** Smeared adhesive and stains can be removed with denatured alcohol or thinner for nitrocellulose lacquer.

# **TECHNICAL SPECIFICATIONS**

Bonding technique:	Wet adhesion
Chemical base:	Acrylic ester/PVC copolymer
Chemicals resistance:	Water, greases, oils, alcohol
Colour:	Crystal clear
Consistency:	Medium viscosity
Density approx.:	0.9 g/cm <sup>3</sup>
Drying/Curing time approx.*:	5-10 minutes
Final bond strength after:	24 hours
Minimum application temperature:	10 °C
Minimum temperature resistance:	-30 °C
Maximum temperature resistance:	90 °C
Moisture resistance:	Good
Solid matter approx.:	20 %
Solvent:	Mixture of esters and ketones
Transparent:	Yes
Viscosity:	Liquid
Viscosity approx.:	2000 mPa·s
Water resistance:	Good

<sup>\*</sup> Curing time may vary depending on a.o. surface, product quantity used, humidity level and ambient temperature.

### **PACK SIZES**

tube 33ml

#### **STORAGE CONDITIONS**

Store in a dry, cool and frost-free place.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.